

## Time-resolved Far-IR Spectroscopy of Quasiparticle Recombination in $\text{BaPb}_{1-x}\text{Bi}_x\text{O}_3$ Films


R.P.S.M. Lobo (ENS, France), E.J. Choi (U. Seoul), D.H. Reitze, D.B. Tanner (U. Florida), and G.L. Carr (BNL, NSLS)

Abstract No. Lobo8146


Beamline(s): U12IR

Oxide superconductors have shown evidence for unusual quasiparticle scattering processes and gap anisotropy, very much different from what is observed for metallic (low  $T_c$ ) superconductors. Both gap anisotropy and scattering manifest themselves in the relaxation of excess quasiparticles. We have studied the generation and relaxation of excess quasiparticles in the oxide superconductor  $\text{BaPb}_{1-x}\text{Bi}_x\text{O}_3$  ( $x \sim 0.25$ ) using time-resolved far-infrared spectroscopy. The samples were thin films, produced by pulsed laser deposition onto MgO substrates. Measurements were performed using the same pump-probe technique developed for the study of Pb and other low  $T_c$  superconductors. Both the excess quasiparticle signal magnitude and relaxation time were measured as a function of temperature. While the excess quasiparticle signal shows a BCS-like behavior, the effective lifetime is found to be 1 ns and independent of temperature to below  $T_c/2$ . While the effective lifetime value is reasonable in magnitude, the lack of any temperature dependence is unexpected. Further studies at lower temperature are planned.

**Acknowledgments:** Research supported by DOE through contract DE-AC02-98CH10886 at the NSLS and DE-FGO2-96ER45584 at the University of Florida.



**Figure 1.** Excess quasiparticle signal as a function of temperature.



**Figure 2.** Effective lifetime for 4 different  $\text{Ba(Pb)BiO}_3$  films. A 1 ns lifetime is found for all temperatures down to below 3K.